In: Sanayei, Masoud, ed. Restructuring: America and beyond: Proceedings of Structures Congress 13; 1995 April 2-5; Boston, MA. New York: American Society of Civil Engineers; 1995: 277-280. Vol. 1.

Evaluation Of Timber Bridges Using Stress Wave Technology

Roy F. Pellerin, [1] Robert J. Ross, [2] Robert H. Falk,[2] Norbert J. Volny,[3]

Summary

The focus of this research was to develop stress wave NDE techniques for determination of the in-place properties and strength of timber bridge components. Current inspection procedures for timber bridges is often an art involving visual assessments of the degree of decay and mechanical damage and of the extent to which the deterioration has penetrated into hidden regions of the structure. NDE techniques utilizing stress waves has successfully been used to improve the assessment of the integrity of wood structures.

The research results show improved stress wave velocity methods that more accurately quantify the residual strength of wood members and the timber bridges themselves. These improved methods have been applied to wood bridges and piles that had been targeted for replacement. Stress wave evaluations were performed on the bridges in-place, followed by destructive testing of elements of the bridges and piles after demolition to verify the NDE conclusions. While the application of the stress wave methods in this study is for softwood timber bridges, the methods are applicable to all timber bridges. The ultimate goal of the research is to develop a comprehensive handbook for bridge inspectors which provides guidelines on the use, application and interpretation of stress wave methodology for locating and defining areas of deterioration in timber bridges. This presentation discusses the theory of stress wave technology, user guidelines for equipment use, interpretive procedures, and procedural guidelines for assigning design values to in-place bridge components and for assessing in-place capacity.

Introduction

It has been estimated by the Federal Highway Administration for the United States that as much as 41% of the nation's bridges are either structurally deficient or in need of repair (Tarricone, 1990). There have been several recent instances of catastrophic collapse and loss of life attributable to deterioration in bridges (Scalzi, 1990). Repair, retrofit, rehabilitation or replacement of severely deteriorated elements of the infrastructure is essential to preserve public safety. A key element in implementing these efforts to improve the infrastructure is the ability to accurately

[1]Washington State University, Pullman, WA, USA
[2]USDA Forest Service, Madison, WI, USA
[3]Volny Engineering, Inc., Bend, OR, USA

evaluate the material properties, degree of deterioration, and remaining life of structural systems.

Current methods of assessing the safety of structures typically rely heavily on visual inspection processes. Based largely on experience and judgment, an engineer will subjectively determine the degree of deterioration and remaining life of a structure. Destructive testing of samples taken from the structure (e.g. coring) will sometimes also be performed to assist in this assessment. Nondestructive evaluation (NDE) methods would clearly assist in evaluating the deterioration and integrity of structures. While many NDE techniques are available for metals, very few methods are available for application to the non-metal materials typically present in structures, such as wood, and concrete. Further, the few NDE methods that are used for structures are typically used on a comparative basis and the results are often unreliable. It is essential that quantitative NDE methods capable of being performed in the field on a routine inspection basis be developed to accurately assess the safety of structures.

The focus of this research is to develop NDE techniques for determination of the in-place properties and strength of wood in a bridge, both above and below ground. Current inspection procedures for timber structures is often an art involving visual assessments of the degree of decay and mechanical damage and of the extent to which the deterioration has penetrated into hidden regions of the structure. NDE techniques utilizing monitoring of stress waves has successfully been used to improve the assessment of the integrity of wood structures. This approach has been employed to inspect wood buildings (Hoyle and Pellerin, 1978), wood piers (Ross and Pellerin, 1991), and the world's largest laminated beam structure - TRESTLE (Brown, 1985; Neal, 1985).

This research quantitatively relates stress wave parameters, such as wave velocity and attenuation, to the residual strength of wood bridge members. The stress wave NDE method has been applied to wood bridges and piles that have been targeted for replacement. The nondestructive evaluations are performed on the bridges in-place, followed by destructive testing of elements of the bridges and piles after demolition to verify the NDE conclusions. While the application of the NDE methods in this study is for bridges, the methods will be generally applicable to wood structures. The ultimate goal of the research is to develop practical techniques for the quantitative NDE of wood structures and to develop a comprehensive handbook for bridge inspectors that provides guidelines on the use, application and interpretation of stress wave methodology for locating and defining areas of deterioration in timber bridges. Particular attention will be given to presenting the theory of stress wave technology describing the necessary instrumentation, defining practical procedures, and preparing interpretation guidelines for the quantitative NDE of timber bridges by inspection personnel.

Background

Considerable research activity has focused on development of techniques to measure stress wave attenuation in wood products (Ross and Pellerin, 1991). The interest in attenuation is because stress wave speed alone is not sufficient to detect different wood degradation with equal sensitivity, as demonstrated by Pellerin et al. (1985). In clear wood degraded under controlled laboratory conditions, stress wave speed parallel to the wood grain was affected by brown rot decay, but not by

subterranean termites which attacked only a specific portion of the wood (i.e., the early wood) in the test beams.

There is extensive literature on the use of stress wave velocity and attenuation for the measuring of elastic properties of wood. This is documented in the reviews by Kaiserlik (1978) and Ross and Pellerin (1991). A main conclusion reached as a result of this extensive research is that the extent of wood decay correlates to the modulus of elasticity. Numerous applications of stress wave NDE methods for the in-place NDE of wood structures are summarized by Ross and Pellerin (1991), including applications to wood buildings, stadiums, piers, bridges, utility poles, and cooling towers.

Simple mechanical NDE techniques have also been used for the in-place inspection of wood members in structures (Ross and Pellerin, 1991). For example, sounding-, pick-, or probing-type tests are used by inspectors of wood structures to indicate the condition of a structural member. The underlying premise for the use of such tests is that degraded wood is relatively soft and will have a low resistance to probe penetration. A quantitative test based on this premise was developed by Talbott (1982). Talbott examined withdrawal resistance of a threaded probe, similar to a wood screw, inserted into a member, which could be correlated to the residual strength of the wood member.

Based on the extensive literature review performed by Ross and Pellerin (1991), the following conclusions on the state-of-the-art NDE techniques for assessing wood structures were reached:

1. Laboratory investigations have established relationships between NDE parameters and the performance of wood members, and the relationships have been verified using a wide range of wood-based materials and a variety of NDE techniques.

2. Laboratory studies of the predictive relationships for biologically degraded wood typical of that actually found in structures have been limited in regards to both the NDE evaluation techniques employed and the biological agents of deterioration studied.

3. In-place assessment efforts have focused primarily on adaptations of stress-wave NDE techniques. These techniques have shown considerable promise, are relatively easy to use, and have low equipment costs. However, the application of stress wave NDE techniques to complicated structures and the effect of structure boundary conditions has not been adequately addressed. Further, little information exists on the relationship between excitation system characteristics and wave behavior.

experimental Procedure

Before beginning the NDE of a bridge, base wave transit times to he expected depending on the member dimensions are determined. A threshold velocity for rot of 635 meters/second is used to establish the transit times. After a quick visual inspection of the timber structure, its members are initially marked at a set interval which is usually 600 mm. The marks are started as close as possible to a member end. NDE of the members is done at the marks vertically through the centerline and

horizontally at the top, center, and bottom. If an anomaly is found, sample spacing is densified to 300 mm intervals and 50 mm o.c. vertically and horizontally. In glulam members each lamination is sampled. This close space sampling is continued until the readings again indicate sound timber.

To verify the stress wave velocity information, increment cores of the timber may be taken at one sound location as well as those locations that stress wave velocity readings indicate are unsound. The increment core data, stress wave velocity data, and moisture contents are transferred to a scale drawing which can then be used in calculating the remaining strengths of the structure and determination of the extent and cost of repairs required.

Bibliography

Browne, C.M. and Kuchar, W.E. 1985. "Determination of Material Properties for Structural Evaluation of TRESTLE." Fifth International Symposium on the Nondestructive Testing of Wood, Washington State University, Pullman, Washington.

Hoyle, R.J. and Pellerin, R.F. 1978. "Stress Wave Inspection of a Wood Structure." Proceedings of the Fourth Nondestructive Testing of Wood Symposium, Washington State University, Pullman, Washington.

Kaiserlik, J.H. 1978. "Nondestructive Testing Methods to Predict Effect of Degradation on Wood, a Critical Assessment." USDA Forest Service General Technical Report FPL-19. Forest Products Laboratory, Madison, Wisconsin.

Neal, D.W. 1985. "Establishment of Elastic Properties for In-Place Structures." Proceedings of the Fifth Nondestructive Testing of Wood Symposium, Pullman, Washington.

Pellerin, R.F., DeGrotte, R.C. and Esenther, G.R. 1985. "Nondestructive Stress Wave Measurements of Decay and Termite Attack in Experimental Wood Units." Proceedings of the Fifth Nondestructive Testing of Wood Symposium, Washington State University, Pullman, Washington.

Ross, R.J. and Pellerin, R.F. 1991. "Nondestructive Testing for Assessing Wood Members in Structures: A Review." USDA Forest Service General Technical Report FPL-GTR-70, Forest Products Laboratory, Madison, Wisconsin.

Scalzi, J.B. 1990. "On the Drawing Board." ASCE Civil Engineering Magazine, May, pp. 65-67.

Talbott, J.W. 1982. Unpublished research. Washington State University, Pullman, Washington.

Tarricone, P. 1990. "Bridges Under Surveillance." ASCE Civil Engineering Magazine, May, pp. 48-51.