



Forest
Service

United States
Department of
Agriculture

FS-237

Six species and one variety of true fir in western North America are commercially important trees whose woods are grouped together and sold as white fir by the wood industry. White fir wood is light in weight and is manufactured primarily into lumber, plywood for construction and industrial use, and wood pulp for paper manufacture. Construction uses include framing, sheathing, concrete forms, roof decking, and siding. Industrial uses include industrial crating and shook, pallet stock, furniture parts, and laminated wood products.

White Fir

An American Wood



White Fir (*Abies* spp.)

Donald C. Markstrom and Sue E. McElderry¹

Commercial Species and Names

North American members of the genus *Abies* are called true firs to distinguish them from Douglas-fir, which belongs to the genus *Pseudotsuga*. There are six species and one variety of true fir in western North America that produce commercially valuable timber. Because of similarities in appearance and properties, the woods of these species are combined and sold as white fir by the wood industry. This term should not be confused with the common name of *Abies concolor*, the white fir tree, whose wood is also included in this lumber group.

In this leaflet, the term white fir group is used when referring to the wood of all species included in the commercial designation. The accepted common name of the tree is used when an individual species is discussed; the accepted common name has been selected by the Tree and Range Plant Name Committee of the U.S. Department of Agriculture Forest Service in an effort to standardize the common names of trees. The following is a list of trees included in the white fir group.

Distribution and Growth Characteristics

All species of the white fir group grow in the Pacific Coast States. Pacific silver fir and subalpine fir extend northward along the coast into southeastern Alaska. In addition to growing in the Pacific Coast States, grand fir also grows in the northern Rockies, extending into British Columbia. Subalpine fir is found throughout the Rocky Mountains and in the Southwest; white fir and corkbark fir are present in the southern Rockies and the Southwest.

In general, the true firs have flattened needles that are 3/4 to 1-1/2 inches long. White fir (fig. 1) has exceptionally long, 2- to 3-inch needles.

Scientific name	Accepted common name	Other names
<i>Abies amabilis</i>	Pacific silver fir	silver fir Cascades fir red fir white fir
<i>Abies concolor</i>	white fir	balsam fir Colorado fir silver fir white balsam
<i>Abies grandis</i>	grand fir	balsam fir giant fir lowland white fir silver fir white fir yellow fir
<i>Abies lasiocarpa</i>	subalpine fir	alpine fir balsam Rocky Mountain fir white fir
<i>A. lasiocarpa</i> var. <i>arizonica</i>	corkbark fir	Arizona fir cork fir white fir
<i>Abies magnifica</i>	California red fir	Shasta red fir red fir silver tip white fir
<i>Abies procera</i>	noble fir	red fir white fir

Unlike the other true firs, needles of noble fir and California red fir are four-sided rather than flattened.

The cones of true firs are cylindrical to barrel-shaped and are borne erect on the uppermost branches. Grand, subalpine, the corkbark firs have cones 2-1/4 to 4-1/4 inches long, while those of California red fir are 6 to 9 inches long. The other trees in this group have cones intermediate in length. When they mature, the cones do not open; instead the scales fall off, releasing the seeds and leaving the spike-like central axes standing on the branch.

Distribution and growth characteristics vary considerably among the individual species and are discussed separately.

White Fir, *Abies concolor* (Gord. & Glend.) Lindl. ex Hildebr.—White fir is found in a variety of climatic situations across its geographic range. At high elevations in the Rocky Mountains, growing seasons are short and the snowpack is moderate to heavy. Summers tend to be wetter in the Southwest than in the central Rockies, where rainfall is distributed more evenly throughout the spring and summer. In the

¹Associate Wood Technologist and Research Forester, respectively, U.S. Department of Agriculture, Forest Service, Rocky Mountain Forest and Range Experiment Station, Fort Collins, Colo.

Coastal States, the growing season is dry. Fall and early spring rains account for most of the precipitation at low elevations, while higher up most moisture comes from winter snowpack. White fir grows at elevations as low as 2,000 feet in Oregon and as high as 11,000 feet in the interior portion of its range (fig. 2).

White fir is commonly found growing with other species that vary with latitude, elevation, and site. In the Coastal States, associates include ponderosa, Jeffrey, and sugar pines; grand and California red firs; Douglas-fir; and incense-cedar. In the Rocky Mountains and Southwest, white fir is found with Douglas-fir, ponderosa pine, blue and Engelmann spruces, quaking aspen, and subalpine and corkbark firs.²

White fir seedlings are shade tolerant, but once established, they grow best in full sunlight. Growth may be slow the first 5 years or longer. In the Coastal States, trees 40 to 65 inches in diameter and 130 to 180 feet tall are not unusual. In the Southwest, trees average about 50 inches in diameter and 135 feet tall. The record white fir is 107 inches in diameter and 192 feet tall. Near the coast, white fir does not often exceed 350 years of age, but 500-year-old individuals have been reported. Maximum ages in the interior may be nearly 300 years.

The most serious pest of white fir is the fir engraver, a beetle that causes considerable damage and mortality. Various defoliators, including the Douglas-fir tussock moth and western spruce budworm, reduce growth and kill some trees.³ Partial cutting, which leaves the tree unprotected by neighbors, or the weakening effects of rot may predispose this shallow-rooted species to windthrow. White fir, like the other true firs, is susceptible to dwarf mistletoe infestation. Browsing

²For the scientific names of these trees and other trees mentioned in this publication, see the appendix.

³For the scientific names of these insects and other insects mentioned in this publication, see the appendix.




Figure 1—Foliage, cone, and bark of white fir (*Abies concolor*).

F-222502

by big game may retard height growth for many years.

Grand Fir, *Abies grandis* (Dougl. ex D. Don) Lindl.—Climate across the range of grand fir is quite variable (fig. 3). Annual precipitation may be as low as 14 inches in eastern Oregon and as high as 100 inches in western Washington. Only 15 to 25 percent of the total precipitation occurs during the growing season. Snowfall is greater in the interior mountains than nearer the coast. Grand fir may be found near sea level in British Columbia and as high as 5,000 feet in portions of Oregon and Idaho.

Grand fir grows in pure stands in north-central Idaho. Elsewhere, it is

usually found in mixture with other species. Its associates include Douglas-fir, western larch, western redcedar, western hemlock, Sitka spruce, redwood, and ponderosa, lodgepole, and western white pines.

Grand fir seedlings are shade tolerant, but after age 20 to 30 years, the most rapid growth is attained in the open. Trees in coastal forests reach 24 to 48 inches in diameter and 140 to 160 feet in height. The record specimen is 79 inches in diameter and 231 feet tall. Rapid early height growth has produced 140-foot trees at 50 years. The maximum reported age is 280 years.

The susceptibility of grand fir to heartrot and decay results in appreciable losses of merchantable volume.

The western spruce budworm and Douglas-fir tussock moth cause widespread defoliation, dieback, and mortality. The fir engraver, western balsam bark beetle, and balsam woolly aphid all contribute to mortality.

California Red Fir, *Abies magnifica* A. Murr.—In the more northern portions of its range the cones of California red fir sometimes have bracts that are longer than the cone scales. Some taxonomists recognize this form as a separate variety named Shasta red fir (*Abies magnifica* var. *shastensis*). However, these two trees are very similar and intermediate forms occur. Recent studies indicate that Shasta red fir is a hybrid between California red fir and noble fir. Therefore, these two trees are not distinguished here, but are referred to collectively as red fir.

The climate over the geographic range of red fir is characterized by heavy winter snowpacks that contain 80 percent or more of the total annual precipitation (fig. 4). The precipitation supplied by scattered summer thunder-showers is negligible, resulting in a 4- to 5-month dry period during the growing season. Over most of its range, red fir grows at elevations between 6,000 and 9,000 feet.

Red fir sometimes forms pure stands. It also may be found in association with Douglas-fir, mountain hemlock, white fir, and ponderosa, Jeffrey, lodgepole, and sugar pines.

Seedlings of red fir are initially shade tolerant, but after establishment, their growth is best in full sunlight. Growth may be slow for the first 5 years or longer. Mature trees commonly attain diameters of 48 to 60 inches and heights of 150 feet. The record specimen is 102 inches in diameter and 180 feet tall. Trees older than 500 years have been reported.

Heartrots result in loss of merchantable volume, and dwarf mistletoe significantly reduces growth. The fir engraver is the most damaging insect pest, but flatheaded and roundheaded fir borers also contribute to mortality. On exposed ridges or after partial cut-




Figure 2—The range of white fir (*Abies concolor*).

F-533460

ting, red fir is susceptible to top breakage and windthrow.

Noble Fir, *Abies procera* Rehd.—Noble fir is found mainly within a superhumid region of relatively cool temperatures and high precipitation (fig. 5). Most of the precipitation falls during the winter, primarily as snow. Over most of its range, noble fir is found at elevations between 3,000 and 5,000 feet.

Noble fir does not form extensive pure stands, but small pure stands are common. It also occurs widely in mixture with other species, most commonly with Douglas-fir, Pacific silver fir, western redcedar, Alaska-cedar, lodgepole and western white pines, and western and mountain hemlocks.

Although seedlings and saplings are moderately shade tolerant, noble fir is considered the least shade tolerant of

the white fir group. Initial seedling growth is typically slower than that of associated species. Seedlings do not develop an early taproot and, therefore, are drought sensitive.

Noble fir attains the largest dimensions of any true fir. The record tree is 108 inches in diameter and 278 feet tall. Mature trees commonly attain diameters of 45 to 60 inches and heights of 130 to 175 feet. This species contains more volume for a given diameter than any of its associates because of its relatively thin bark, slight taper, and large size.

Noble fir is considered the longest lived of the white fir group, with some individuals exceeding 600 years. Mature trees are relatively free of serious insect and disease problems. Noble fir is windfirm because of its deep, spreading root system.

Pacific Silver Fir, *Abies amabilis* Dougl. ex Forbes—Climate throughout the geographic range of Pacific silver fir is characterized by moderate temperatures, humid conditions, a long growing season, and a short, late summer dry period (fig. 6). Winter snowpacks at higher elevations are generally heavy. Pacific silver fir may be found near sea level at the western edge of its range, and up to 6,000 feet in the Cascade Range of south-central Oregon.

This species may form nearly pure stands or grow in mixture with other species. Its associates include western and mountain hemlocks, Douglas-fir, Sitka spruce, and subalpine fir. From seedling to maturity, Pacific silver fir is probably the most shade tolerant of the white fir group.

Seedling growth is very slow, especially in dense shade. Trees 24 or more inches in diameter and 180 to 200 feet tall are common in old growth stands. The record specimen is 101 inches in diameter and 245 feet tall. The maximum age reported for Pacific silver fir is 590 years.

The balsam woolly aphid causes serious mortality in Pacific silver fir. The silver fir beetle and fir root bark beetle also contribute to mortality, and the western hemlock looper and black-




Figure 3—Range of grand fir (*Abies grandis*).

F-533400

headed budworm cause serious defoliation. This species has shallow roots and is susceptible to windthrow, especially after partial cutting.

Subalpine Fir, *Abies lasiocarpa* (Hook.) Nutt. var. *lasiocarpa*, and **Corkbark Fir, *Abies lasiocarpa* var. *arizonica* (Merriam) Lemm.**—This species is more widely distributed than the other western firs (fig. 7). Subalpine fir has thin, smooth bark, and is found extensively from the Yukon Territory to the Kaibab Plateau in northern

Arizona. Corkbark fir, with its thick, corky bark, is restricted to New Mexico, Arizona, and southwestern Colorado, where it occurs with subalpine fir. Because corkbark fir is a variety of subalpine fir, where appropriate, the two will be referred to collectively as subalpine fir.

Subalpine fir is primarily a high elevation species that may be found as high as 12,000 feet in the southern portion of its range. However, at the northern limits of the distribution, it

may be found near sea level. The climate across its range is characterized by short, cool growing seasons and long, generally cold winters with heavy snowpacks.

Limited pure stands of subalpine fir may be found, but it most commonly occurs in mixture with other species. Engelmann spruce is its most common associate in the northern Cascades and throughout the Rocky Mountains. Other associates include mountain hemlock, white and Pacific silver firs, lodgepole and whitebark pines, and quaking aspen.

Shade is important for establishment and early survival of subalpine fir. Early growth is very slow; under favorable conditions, trees reach only 4 to 5 feet in height at 20 to 40 years of age. Mature subalpine firs are typically 12 to 24 inches in diameter and 40 to 100 feet tall with long, narrow, spirelike crowns. The record corkbark fir is 50 inches in diameter and 95 feet tall; the largest known subalpine fir is 80 inches in diameter and 130 feet tall. Trees often live for more than 250 years. On exposed sites near timberline, subalpine fir is often reduced to a stunted shrub form.

The most destructive insect pests of subalpine fir include the western spruce budworm, balsam woolly aphid, western balsam bark beetle, and the fir engraver. Many trees either die or are complete culls at an early age because of various wood-rotting fungi. The species is also susceptible to windthrow, which may be aggravated by topographic exposure and partial cutting.

Supply

The total stand of the sawtimber-size white fir group in the western United States is estimated to be 215 billion board feet. By regions, about 41 percent of the total stand is in the Pacific Northwest, 34 percent in the Pacific Southwest, 18 percent in the northern Rocky Mountains, and 7 percent in the southern Rocky Mountains. By States, about 34 percent of the total stand is in California, 21 percent in Washington, 20 percent in Oregon, and 14 percent in




Figure 4—The range of California red fir (*Abies magnifica*).

F-533403

Idaho. The remaining 11 percent occurs in other Western States.

Production

Lumber production of the white fir group has fluctuated widely, generally increasing from 1905 to the mid-1960's (fig. 8). Production rose spectacularly from approximately 121 million board feet in 1940 to a record of 2,838 million board feet in 1959. Production since 1959 has lessened and been variable. About 78 percent of the total lumber production in 1976 came from California, Oregon, and Washington. The average production of lumber for the period 1970 through 1979 inclusive was 2,170 million board feet per year. The net annual cut of the white fir group from growing stock during 1976 was estimated at 503 million cubic feet.

Characteristics and Properties

The wood of the white fir group is nearly white to reddish brown, with little or no difference between the sapwood and heartwood. The annual rings show a marked difference in color between the latewood and the earlywood of the succeeding year. The transition from earlywood to latewood is gradual. The wood of this group has a medium to somewhat coarse texture and no normal resin canals. Most of the woods of this group have no characteristic taste or odor when dried, but subalpine fir can have a characteristic odor when damp or when it is rewetted. Wood of the white fir group appears similar to that of western hemlock, except that the color transition from the lighter earlywood to the darker latewood is typically more abrupt in the white firs.

The wood is generally straight grained, relatively easy to work, and stays in place when properly dried. It is one of the important lighter commercial woods of the United States, having an average specific gravity based on green volume and oven-dry weight ranging from 0.31 to 0.40, depending on the species. The weight of the white fir group, excluding subalpine fir, averages 27 pounds per cubic foot at 12 percent




Figure 5—The range of noble fir (*Abies procera*).

F-533402

moisture content; subalpine fir weighs 23 pounds per cubic foot at 12 percent moisture content. The wood is moderate to moderately low in strength, stiffness, ability to resist shock, and in nail withdrawal resistance. The lumber is normally easily dried, but wetwood, a condition caused by bacterial infection, occasionally causes problems that require special handling during the drying process.

In paint-holding properties, the white fir group is classed with ponderosa pine and western hemlock—below sugar, western white, and eastern white pines, western redcedar, redwood, and baldcypress, but above Douglas-fir and shortleaf, slash, longleaf, loblolly, and Virginia pines. The white fir group, like western redcedar and redwood, is easily glued under a wide range of conditions. The heartwood is not durable when

used under conditions favorable to decay; in this, it ranks with spruce and hemlock. As with practically all other species, the sapwood lacks durability. The wood is considered difficult to penetrate with preservatives.

The lumber from some of the white fir group, especially subalpine fir, is quite likely to contain small knots formed by numerous, persistent small limbs. Consequently, these species yield only minor amounts of high-grade lumber.

Principal Uses

The white fir group is primarily used for lumber, plywood, and pulp in the manufacture of paper. Most of the lumber and plywood is used for construction. For example, during 1965, lumber production reached 2,416 million board feet, and only 380 million was used in remanufacture by industry. Construction uses include framing, sheathing, subflooring, concrete forms, decking, planking, beams, posts, siding, and paneling. Industrial uses include production of millwork, prefabricated buildings and structural members, industrial crating and shook, furniture parts, and mobile homes. Because of its light weight and color, it is especially suitable for fresh fruit and vegetable containers.

All trees in the white fir group can be pulped by any process as easily as spruce, and except for red fir, compare favorably in pulp quality. Red fir yields darker mechanical pulp, and its sulfite and sulfate pulps are more difficult to bleach than those from spruce. The sulfite pulp is suitable for the manufacture of newsprint, light-colored wrapping, book, and other high-grade printing papers. The sulfate pulp is suitable for high-grade kraft wrapping papers and fiberboard. The groundwood pulp is suitable for all uses requiring this type of pulp.




Figure 6—The range of Pacific silver fir (*Abies amabilis*).

F-533401




Figure 7—The range of subalpine fir (*Abies*)

F-533461

Appendix

Common and scientific names of associated trees and insects mentioned in the text.

Trees

Accepted common names

Alaska-cedar
western larch
incense-cedar

Engelmann spruce
blue spruce
Sitka spruce
whitebark pine
lodgepole pine
Jeffery pine

ponderosa pine
quaking aspen
Douglas-fir
redwood
baldcypress

western redcedar
western hemlock
mountain hemlock

shortleaf pine
slash pine
longleaf pine
loblolly pine
Virginia pine
sugar pine
western white pine

eastern white pine

Insects

Accepted common name

western blackheaded budworm
balsam woolly adelgid
western spruce budworm

western balsam bark beetle
western hemlock looper
flatheaded fir borer
Douglas-fir tussock moth
fir root bark beetle
silver fir beetle
fir engraver
roundheaded fir borer

Scientific name

Chamaecyparis nootkatensis
Larix occidentalis
Libocedrus decurrens

Picea engelmannii
Picea pungens
Picea sitchensis
Pinus albicaulis
Pinus contorta
Pinus jeffreyi

Pinus ponderosa
Populus tremuloides
Pseudotsuga menziesii
Sequoia sempervirens
Taxodium distichum

Thuja plicata
Tsuga heterophylla
Tsuga mertensiana

Pinus echinata
Pinus elliottii
Pinus palustris
Pinus taeda
Pinus virginiana
Pinus lambertiana
Pinus monticola

Pinus strobus

Scientific name

Acleris gloverana
Adelges piceae
Choristoneura occidentalis

Dryocoetes confusus
Lambdina fuscicollis lugubrosa
Melanophila drummondii
Orgyia pseudotsugata
Pseudohylesinus granulatus
Pseudohylesinus sericeus
Scolytus ventralis
Tetropium abietis




Figure 8—Lumber production of the white fir group, 1905-79.

References

- Alexander, Robert R. *Silviculture of subalpine forests in the central and southern Rocky Mountains: The status of our knowledge.* Res. Pap. RM-121. Fort Collins, CO: U.S. Department of Agriculture, Forest Service, Rocky Mountain Forest and Range Experiment Station; 1974. 88 p.
- American Forestry Association. *The AFA national register of big trees.* *American Forests* 84(4):17-47; 1978.
- Franklin, Jerry F.; Dyrness, C. T. *Natural vegetation of Oregon and Washington.* Gen. Tech. Rep. PNW-8. Portland, OR: U.S. Department of Agriculture, Forest Service, Pacific Northwest Forest and Range Experiment Station; 1973. 417 p.
- Fowells, H. A., comp. *Silvics of forest trees of the United States.* Agric. Handb. 271. Washington, DC: U.S. Department of Agriculture; 1965. 762 p.
- Furniss, R. L.; Carolin, V. M. *Western forest insects.* Misc. Publ. 1339. Washington, DC: U.S. Department of Agriculture; 1977. 654 p.
- Gill, Thomas G.; Phelps, Robert B. *Wood used in manufacturing industries, 1965.* Stat. Bull. 440. Washington, DC: U.S. Department of Agriculture; 1969. 101 p.
- Gjovik, Lee R.; Baechler, Roy H. *Selection, production, and use of preservative-treated wood, supplementing federal specification TT-W-571.* Gen. Tech. Rep. FPL-15. Madison, WI: U.S. Department of Agriculture, Forest Service; 1977. 37 p.
- Gordon, Donald T. *Released advanced reproduction of white and red fir—growth, damage, mortality.* Res. Pap. PSW-95. Berkeley, CA: U.S. Department of Agriculture, Forest Service, Pacific Southwest Forest and Range Experiment Station; 1971. 12 p.
- Harlow, William M.; Harrar, Ellwood, S.; White, Fred M. *Textbook of dendrology.* 6th ed. New York: McGraw-Hill; 1979. 510 p.
- Hepting, George H. *Diseases of forest and shade trees of the United States.* Agric. Handb. 386. Washington, DC: U.S. Department of Agriculture; 1971. 658 p.
- Jones, John R. *Silviculture of southwestern mixed conifers and aspen: The status of our knowledge.* Res. Pap. RM-122. Fort Collins, CO: U.S. Department of Agriculture, Forest Service, Rocky Mountain Forest and Range Experiment Station; 1974. 44 p.
- Krajina, V. J. *Ecology of forest trees in British Columbia.* *Ecology of Western North America* 9(1):1-146; 1969.
- Little, Elbert L., Jr. *Atlas of United States trees. Volume 1: Conifers and important hardwoods.* Misc. Publ. 1146. Washington, DC: U.S. Department of Agriculture; 1971. 211 p.
- Liu, Tang-Shui. *A monograph of the genus *Abies*.* Taipei, Taiwan, China: National Taiwan University, College of Agriculture, Department of Forestry; 1971. 698 p.
- Minor, Don. *Comparative autecological characteristics of northwestern tree species—a literature review.* Gen. Tech. Rep. PNW-87. Portland, OR: U.S. Department of Agriculture, Forest Service, Pacific Northwest Forest and Range Experiment Station; 1979. 72 p.
- Panshin, A. J.; de Zeeuw, Carl. *Textbook of wood technology.* 3d ed. Vol. 1: Structure, identification, uses, and properties of the commercial woods of United States and Canada. New York: McGraw-Hill; 1970. 705 p.
- Schopmeyer, C. S., tech. coord. *Seeds of woody plants in the United States.* Agric. Handb. 450. Washington, DC: U.S. Department of Agriculture; 1974. 883 p.
- Stear, Henry B. *Lumber production in the United States 1799-1946.* Misc. Publ. 669. Washington, DC: U.S. Department of Agriculture; 1948. 223 p.
- U.S. Department of Agriculture, Forest Service. *An analysis of the timber situation in the United States 1952-2030.* Forest Resource Report No. 23. Washington, DC: U.S. Department of Agriculture; 1982. 528 p.

U.S. Department of Agriculture, Forest Service, Forest Products Laboratory. Wood handbook: wood as an engineering material. Agric. Handb. 72. Rev. ed. Washington, DC: U.S. Department of Agriculture; 1974. 428 p.

U.S. Department of Commerce, Bureau of the Census. Lumber production and mill stocks. Current Industrial Reports, Series M24T and MA24T. Washington, DC: U.S. Department of Commerce, Bureau of the Census.

Ward, J. C.; Pong, W. Y. Wetwood in trees: a timber resource problem. Gen. Tech. Rep. PNW-112. Portland, OR: U.S. Department of Agriculture, Forest Service; 1980. 56 p.